



AA Composites - P:+61444568646

Platinum 360+ Epoxy Instructions & Info

Non Toxic, Food Grade & Non Dangerous Goods

Mix 2:1 by Volume

360+ Epoxy Resin is one of our newest resins using our latest third generation technology. Originally for surfboards, but an ideal resin, 360+ has high UV, rock hard high gloss surface, there are so many brilliant uses for 360+; such as coasters, mugs, plates etc. - once cured it can be put through the microwave and dishwasher with no changes or effects to the resin or the product! 360+ is a crystal clear epoxy, FDA food grade approved and non toxic!

Mix 2 parts A to 1 Part B by volume. Mix resin and hardener together, the resin will go cloudy? but keep mixing until resin goes back to clear *try to mix by hand*. Make sure all of the product has been mixed, including scraping the sides of the mixing container. Pour resin and allow to cure.

Depth of Resin: 360+ can be used to coat and can be poured to a maximum depth of 12mm

Setting time of Resin: Working time: 35 Minutes

Initial Cure: 2.5 Hours

Full Cure: 24 Hours

360+ will not set below 6 deg C, (360+ is tested at 25 deg C, 40% humidity & using 100 gram sample). Platinum 360+ works best on cooler days by heating the resin in the sun or warming the bottles in hot tap

Contact: In Australia / NZ - AA Composites - admin@aacomposites.cc

In USA / Canada - Platinum Epoxies LLC - sales@platinumeponies.com

In Europe - sales@platinumeponies.com