

# AA Composites - 0444568646

## Silcion Moulding Compound

### Instructions & Info

100:2 by weight or 100:3 by weight

Silicon Moulding Compound is used to create moulds.

**Mix:** 100 part A with 2 Parts B by WEIGHT

**Pot Life:** 30 Minutes

**Cure:** 4-6 Hours

**Mix:** 100 part A with 3 Parts B by WEIGHT

**Pot Life:** 25 Minutes

**Cure:** 2-3 Hours

\*Please note that the resin times are based on 25°C lab tested results and will vary on depth of pour and temperature.

Resin will not set below 10°C, and will take longer in a cooler environment, make sure on cooler days that the resin is in the sun or near heat, you can warm the bottles in hot tap water before pouring to allow the resin to heat up a bit.